

JOINTING SOCKET

(WH-ABS005 - 25mm)

Connects two pieces of aspirating smoke detection pipe together. This device is designed for aspirating fire detection only.

Installation Instructions:

Use the correct solvent Plusbond 3019.

Do not paint.

Keep pipe clean and free from dust.

Do not install in direct sunlight.

Only install with approved pipe.


Do not use solvents to clean,


only soapy water.

Part No. WH-ABS005-25


Pipe colour WHITE

Diameter Tolerance +/- 0.15mm





Side Elevation



Noched Izod Impact 73°F(23°C), 0.126 in (3.20 mm), 5.5 ft·lb/ii 73°F(23°C), 0.252 in (6.40 mm), 4.8 ft·lb/ir

Test Method ASTM D256

Test Method ASTM D790

RAW MATERIAL DATA

Acrylonitrile Butaduene Styrene

Kumho ABS 750

Specific Gravity 1.04 Test Method ASTM D792

Molding Shrinkage -Flow 0.0040 to 0.0070 in/in Test Method ASTM D955

Test Method ASTM D638

Tensile Elongation

Flexural Modulus Yield, 73°F (23°C) 0.118 in (3.00 mm) 312000 psi

1.97 in (50.0 mm), 15%

Test Method ASTM D638

Test Method ASTM D638

Flexural Strength Yield, 73°F (23°C) 0.118 in (3.00 mm)

Mechanical: Tensile Strength Yield, 73°F (23°C) 1.97 in (50.0mm)

6670 psi

Melt Mass - Flow Rate (MFR) 200°C/21.6 kg 47 g/10 min 200°C/5.0 kg 4.1 g/10 min 220°C/10.0 kg 34 g/10 min Test Method ASTM D1238

9230 psi

Rockwell Hardness (R-Scale) 108 Test Method ASTM D785

Deflection Temperature Under Load 264 psi (1.8 MPa), Unanneald 185°F/85°C Test Method ASTM D648

Vicat Softening Temperature 203°F/95°C Test Method ASTM D1525

Flamibility

Flame Rating 0.0630 in (1.60 mm) HB 0.0866 in (2.20 mm) HB

Test Method UL 94

Bisson Ltd Unit 11, Eldonwall Trading Estate, St.Phillips, Bristol, BS4 3QQ

Tel: 0117-967-9999 Fax: 0117-961-9261